


(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
19 September 2002 (19.09.2002)

PCT

(10) International Publication Number
WO 02/073155 A1

- (51) International Patent Classification: G01N
- (21) International Application Number: PCT/IB01/00478
- (22) International Filing Date: 9 March 2001 (09.03.2001)
- (25) Filing Language: English
- (26) Publication Language: English
- (71) Applicants and
(72) Inventors: NABIEV, Igor [RU/FR]; 01D, avenue Georges Clémenceau, F-51100 Reims (FR). SUKHANOVA, Alyona [RU/FR]; 6, rue du Docteur Jacquinais, F-51100 Reims (FR). ARTEMYEV, Mikhail [BY/BY]; 54 ul. Kalinovskogo, bt. 3, Appt. 47, Minsk (BY). SHARAPOV, Oleg [UA/UA]; 24-71 prospect 50 Let VLKSM, Kharkov, 31011 (UA). BARANOV, Alexandre [RU/RU]; 128 ul. Bukharestskaya, St.Petersburg (RU). JARDILLIER, Jean-Claude [FR/FR]; 22, rue de la Justice, F-51100 Reims (FR).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- Published:
— with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.
- (74) Agent: DAWIDOWICZ, Armand; Cabinet Dawidowicz, 18, boulevard Pereire, F-75017 Paris (FR).

(54) Title: ULTRASENSITIVE NON-ISOTOPIC WATER-SOLUBLE NANOCRYSTALS




(57) Abstract: The invention concerns a water-soluble semiconductor nanocrystal comprising semiconductor core and shell as well as a cap of one or more additional compounds comprising water-solubilization agents. The invention is characterized in that the water-solubilization agent is chosen in the group consisting of: hydroxamates or derivatives of hydroxamic acid or a combination thereof, multidentate complexing agents or a combination thereof, a bilayer of a TOPO layer attached to the surface of the nanocrystal and an appropriate surfactant layer, a polymeric bead comprising carboxylic groups or amino groups or a combination thereof at the surface of the bead comprising one or more nanocrystal embedded within, a molecule of structural formula $(R^1)_a-R^2-\{(R^3)_b(R^4)_c\}d$. Application to non-isotopic detection systems.

BEST AVAILABLE COPY

WO 02/073155 A1



Français 
1 of 1

Images Description and Claims (76 Kb)

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(11) WO 02/073155

(13) A1

(21) PCT/IB01/00478

(22) 09 March 2001 (09.03.2001)

(25) English (26) English

(43) 19 September 2002 (19.09.2002)

(51) G 01N A

(54) **ULTRASENSITIVE NON-ISOTOPIC WATER-SOLUBLE NANOCRYSTALS**

(71) NABIEV, Igor [RU/FR]; 01D, avenue Georges Clémenceau, F-51100 Reims

(72) (FR). SUKHANOVA, Alyona [RU/FR]; 6, rue du Docteur Jacquinais, F-51100 Reims (FR). ARTEMYEV, Mikhail [BY/BY]; 54 ul. Kalinovskogo, bt. 3, Appt. 47, Minsk (BY). SHARAPOV, Oleg [UA/UA]; 24-71 prospect 50 Let VLKSM, Kharkov, 31011 (UA). BARANOV, Alexandre [RU/RU]; 128 ul. Bukharestskaya, St.Petersburg (RU). JARDILLIER, Jean-Claude [FR/FR]; 22, rue de la Justice, F-51100 Reims (FR).

(74) DAWIDOWICZ, Armand; Cabinet Dawidowicz, 18, boulevard Pereire, F-75017 Paris (FR).

(81) AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW


(84) ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG)

For information on time limits for entry into the national phase please click here

Published

-- with international search report

(57) The invention concerns a *water-soluble* semiconductor nanocrystal comprising semiconductor core and shell as well as a cap of one or more additional compounds comprising water-solubilization agents. The invention is characterized in that the water-solubilization



agent is chosen in the group consisting of:
hydroxamates or derivatives of hydroxamic acid or a combination thereof,
multidentate complexing agents or a combination thereof, a bilayer of a TOPO layer
attached to the surface of the nanocrystal and an appropriate surfactant layer, a
polymeric bead comprising carboxylic groups or amino groups or a combination
thereof at the surface of the bead comprising one or more nanocrystal embedded
within, a molecule of structural formula $(R1)a-R2-\{(R3)b(R4) c\}d$. Application to
non-isotopic detection systems.



Français 

1 of 1

be same or different or can be linked to form a six-, seven-, eight-, nine- or ten- membered cycloalkyl, cycloalkenyl, heterocyclic, aryl, heteroaryl or a six- to thirty membered crown ether or heterocrown ether ; R2 is selected from a bond, a branched or unbranched alkylene, a branched or unbranched heteroalkylene, cycloalkyl, cycloalkenyl, heterocyclic aryl and heteroaryl, R3 is selected from a branched or unbranched alkylene, a branched or unbranched alkenylene, a branched or unbranched heteroalkylene, a branched or unbranched heteroalkenylene, cycloalkyl, cycloalkenyl, cycloalkynyl, heterocyclic aryl and heteroaryl, R4 is selected from the group consisting of an hydrogen, a carboxylate, a thiocarboxylate, an amine, an amide, an imine, an hydrazine, a sulfonate, a sulfoxide, a phosphate, a phosphonate, a phosphonium, an alcohol, a thiol, an ammonium, an alkyl ammonium, a nitrate, a sugar moiety and a five, six, seven, eight, nine, ten-membered cycloalkyl, cycloalkenyl, cycloalkynyl, heterocyclic aryl or heteroaryl, a being 1,2, 3 or 4, b being 0,1,2 or 3, c being 0,1,2 or 3, d being 0,1,2 or 3.

WO-A-00/17642 describes a composition comprising fluorescent semiconductor nanocrystals associated to a compound, the spectral emission of the nanocrystals providing information about a biological state or event, the nanocrystals being *water-soluble* because of a ligand having at least a linking group linked to the nanocrystal and an hydrophilic group.

WO-A-00/29617 describes *water-soluble* luminescent quantum dot and biomolecular conjugate thereof for *ultrasensitive* non- isotopic detection in vitro and in vivo. The *water-soluble* luminescent quantum dot comprises a core consisting of a nanoparticle-sized semiconductor (CdS or CdSe), a cap consisting of a semiconductor differing from the one of the core (ZnS or CdS) and an hydrophilic attachment group consisting of any organic group that can be attached to the surface of the cap and renders the quantum dot *water-soluble*.

The binding between the cap and the hydrophilic attachment group is realised via a sulfur atom.

The *water-soluble* luminescent semiconductor quantum dot can then be linked directly or indirectly with a biomolecule like a protein, a fragment of protein or a nucleic acid, via the hydrophilic attachment group.

The aim of the present invention is to propose a water- soluble nanocrystal prepared with novel solubilisation agents and the method of water-solubilisation of the nanocrystals.

Also provided are *water-soluble* semiconductor nanocrystals probes for biological application wherein the probes are able of providing a detectable electron paramagnetic resonance (EPR) signal or a fluorescence signal or a combination thereof in response to exposure to electromagnetic radiation.

The *water-soluble* semiconductor nanocrystal according the invention comprises semiconductor core and shell as well as a cap of one or more additional compounds comprising water- solubilization agents, and is characterized in that the water-solubilization agent is chosen in the group consisting OF : - HYDROXAMATES or derivatives of hydroxamic acid or a combination thereof, - multidentate complexing agents or a combination thereof, - A bilayer of a TOPO layer attached to the surface of the nanocrystal and an appropriate surfactant layer, - A polymeric bead comprising carboxylic groups or amino groups or a combination thereof at the surface of the bead comprising one or more nanocrystals embedded within, - A molecule of the structural formula (R) A~R- {(R3)(R) B

(R) C} D. The core is a semiconductor nanoparticle. While any core of the IIA-VIB, IIIA-VB or IVA-VIB semiconductors can be used, the core must be such that a luminescent quantum dot results upon combination with a shell. The core is preferably CdSe or ZnSe.

The shell is a semiconductor that differs from the one of the core and bonds to the core and is preferably a IIA-VIB semiconductor of a band gap higher than the core band gap, preferably ZnS, CdS or ZnSe.

According to one embodiment of the invention, the water- solubilizing agent is hydroxamate or a derivative of hydroxamic acid or a combination thereof.

Accordingly, nanocrystal powder is dissolved in an aliphatic solvent and then mixed with a water solution of derivative of hydroxamic acid, the aliphatic layer containing the nanocrystals is extracted and the nanocrystals are precipitated by addition of an alcohol solvent, the precipitate being then dried to powder or dissolved in water.

The invention also provides that the multidentate complexing agent as WATER-SOLUBILIZING agent includes derivatives of ethylenediamine, diethylenetriamine, triethylenetetramine, tetraethylenepentaamine including multidentate acids, amines, thiols, phosphines, phosphates, phosphinoxides or a combination thereof.

Accordingly, nanocrystal powder is dissolved in an aliphatic solvent and then mixed with a water solution of multidentate complexing agents or a combination thereof, the aqueous layer containing the nanocrystals is extracted and the nanocrystals are precipitated by addition of an alcohol solvent, the precipitate being then dissolved in water.

According to the invention, the water-solubilisation agent can also be the molecule of structural formula (RL) A-R {(R3) B (R4) C} D WHEREIN : R1 IS selected from the group consisting of heteroalkyl, heteroalkenyl, heteroalkynyl, -SR, -NHR, -NR2, -N (O) HR, - N (O) R2, -PHR, -PR2, -P (NR2), -P (O) R2, -P (O) (NR2) NR2, - P (O) (OR) POR, -P (O) OR, -P (S) (OR) OR, -P (S) OR, -P (S) SH, -P (S) SR, - C (S) SH, -C (S) SR, wherein R is Li, Na, K; Rb, Cs, NH₄, PH₄, R2 is selected from a bond, a branched or unbranched alkylene, a branched or unbranched alkenylene, a branched or unbranched heteroalkylene, a branched or unbranched heteroalkenylene, cycloalkyl, cycloalkenyl, heterocyclic aryl and heteroaryl, R3 is selected from a branched or unbranched alkylene, a branched or unbranched alkenylene, a branched or unbranched heteroalkylene, a branched or unbranched heteroalkenylene, cycloalkyl, cycloalkenyl, cycloalkynyl, heterocyclic aryl and heteroaryl, R4 is selected from the group consisting of hydrogen, a carboxylate, a thiocarboxylate, an amine, an amide, an imine, an hydrazine, a sulfonate, a sulfoxide, a phosphate, a phosphonate, a phosphonium, an alcohol, a thiol, an ammonium, an alkyl ammonium, a nitrate, a sugar moiety and a five, six, seven, eight, nine, ten-membered cycloalkyl, cycloalkenyl, cycloalkynyl, heterocyclic aryl or heteroaryl, a being 1,2,3 or 4, b being 0,1,2 or 3, c being 0,1,2 or 3, d being 0, 1,2 or 3.

The invention also provides the process for water- solubilisation of the nanocrystals with TOPO (trioctylphosphine oxide) and SDS. The nanocrystals are dissolved in tetrahydrofuran to which an appropriate surfactant molecules such as sodium dodecyl sulfate (SDS) is added, the mixture is stirred few hours, the solvent is evaporated at room temperature and the resulting powder is dissolved in water under ultrasonic treatment.

The invention has for further object the process for the preparation of polymeric *water-*

soluble bead capped with carboxylic groups, comprising one or more nanocrystals embedded within the polymeric matrix characterized in that nanocrystals are dissolved in a mixture of appropriate monomers, a radical initiator is added, the emulsion is prepared in water, containing surfactant, and polymerised at 60-90°C within few hours under vigorous stirring, the polymeric beads being isolated by centrifugation and re- dissolved in water.

Preferably, the nanocrystal according the invention is doped with paramagnetic ions such as Mn^{2+} and other transition or rare-earth ions.

To this purpose, the process for the fabrication of doped nanocrystals with paramagnetic ions is characterised in that TOPO is dried and degassed at 180°C for approximately 1 hour under argon atmosphere, a solution of elemental semiconductors and paramagnetic ions in TOP (tri-n-phosphine) is added to this melt at 350°C, the reaction mixture is then cooled to 300°C and a second solution of semiconductors is added and the reaction mixture is then cooled to 105°C, finally the semiconductor core and shell doped with paramagnetic ions are precipitated and washed with methanol and dissolved with hexane, heptane or tetrahydrofuran or dried to powder.

The invention also provides a **water-soluble** nanocrystal probe comprising a semiconductor nanocrystal, a water- solubilisation agent, a linking agent and an affinity moiety which is able to bound specifically to detectable biological substances, characterized in that the **water-soluble** nanocrystal is one according to the invention. According to one embodiment, the linking agent is able to connect the **water-soluble** nanocrystal or the polymeric bead comprising one or more nanocrystals embedded within with the affinity molecules including peptides, proteins, monoclonal or polyclonal antibodies and their functional fragments, oligonucleotides, RNA, single and double stranded DNA, RNA- DNA hybrid molecules, DNA triplexes and multiplexes and carbohydrates which are able to bound specifically to detectable biological substances, e. g. proteins, oligonucleotides, DNA, RNA, viruses, bacteria, cells, including living cells and tissues.

Preferably, the water-solubilisation agent is also the linking agent.

The nanocrystals probes consisting of polymeric beads should have the same field of application as widely used known Nanofluorospheres comprising organic dyes molecules embedded in the polymeric beads. Advantages of the polymeric beads with the embedded nanocrystals doped or undoped with the paramagnetic ions, compared with the Nanofluorospheres are as follows : -100-FOLD improved stability of nanocrystals against photo- bleaching as compared to organic dyes ; - possibility of multicolour labelling using the nanocrystals of different diameters and of different core and shell ; - possibility of using probes comprising nanocrystals doped with the paramagnetic ions as fluorescence or magnetic resonance probes or as a combination thereof.

The invention further comprises the method of detection of biological substances by registration of EPR signal from paramagnetic ions incorporated into the nanocrystals or of fluorescence signal from the nanocrystals or a combination thereof or by the construction of the images of biological substances by fluorescence or EPR microscopy or by a combination thereof.

The biological imaging is provided by scanning the object by following ways : - VIA detection of spatial distribution of the nanocrystal fluorescence by fluorescence microscopy,

- VIA detection of the EPR signal with high spatial resolution by technique analogous to the scanning tunnel microscopy with a ferromagnetic crystal needle producing the local magnetic field (Hochi A, Furusawa M, Ikeya M, Applications of microwave scanning ESR microscope : human tooth with metal.

Appl Radiat Isot 1993 Jan-Feb; 44 (1-2) : 401-405) or by cavity technique with the use of a narrow aperture for penetration of the microwave electromagnetic field in the object; - VIA simultaneous detection of the EPR signal with high spatial resolution and of the fluorescence signal with high spatial resolution.

The invention will be further described in more details in reference to the following examples and to the annexed drawing wherein : Figure 1 is a schematic illustration of the doped nanocrystals of the invention ; Figure 2a is a schematic illustration of the water-solubilisation of the nanocrystals with hydroxamates of amino acids or with compounds possessing hydroxamic acid functional group.

Figure 2b is a schematic illustration of the water- solubilisation of the nanocrystals with the multidentate complexing agent.

Figure 2c is a schematic illustration of the water- solubilisation of the nanocrystals with the bilayer of TOPO and sodium dodecyl sulfate (SDS).

Figure 2d is a schematic illustration of the water- solubilisation of the nanocrystals by incorporation of one or more TOPO-capped nanocrystals into polymeric bead.

Figure 3a is a schematic illustration of anchoring of the affinity molecules to the *water-soluble* nanocrystal capped with the hydroxamate of amino acid or with compounds possessing hydroxamic acid functional group.

Figure 3b is a schematic illustration of anchoring of the affinity molecules to the *water-soluble* nanocrystal capped with the multidentate complexing agent.

Figure 3c is a schematic illustration of anchoring of the affinity molecules to the *water-soluble* nanocrystal capped with the bilayer of TOPO an SDS.

Figure 3d is a schematic illustration of anchoring of the affinity molecules to the polymeric beads activated with the carboxylic groups and comprising TOPO-capped nanocrystals.

Figure 4 is a schematic representation of the use of water- soluble nanocrystal probe of the invention linked with the affinity molecule for *ultrasensitive non-isotopic* detection and analysis of a detectable substance in a biological material by fluorescence or by electron paramagnetic resonance (EPR) technique or by the combination thereof.

Figures 5a, 5b, 5c are examples of applications of the water- soluble nanocrystals probes according the invention for detection of biological objects.

The following examples serve to illustrate the present invention and are not intended to limit the scope of the invention.
EXAMPLE 1 : FABRICATION OF NANOCRYNTALS OF THE INVENTION doped with Mn²⁺ ions.

12 g of TOPO placed in a three-neck flask are dried and degassed at 180°C for approximately 1 hour under the argon atmosphere. The solution of elemental selenium, dimethylcadmium and bis (phenyl selenide manganese) in 1,2 ml TOP was added under vigorous stirring to this melt at 350°C.

The relative molar concentration of Cd/Se/Mn in TOP is 1,0/0,9/<0,05. The cadmium content in TOP is within the range of 0,1 mmol. After addition of TOP solution, the reaction mixture is cooled to 300°C and the second solution of dimethylzinc and of hexamethyldisilthiane in 2 ml TOP was added. The relative molar concentration of Cd/Zn in final mixture is about 1/4. After adding of the second TOP solution, the reaction mixture is cooled down to 105°C and allowed to stir another 1,5 hours. Finally, CdSe nanocrystals doped with Mn ions and capped with ZnS shell are precipitated with methanol, washed with methanol and dissolved in hexane, heptane, tetrahydrofuran or dried to powder. (figure 1) Example 2 : WATER-SOLUBILISATION OF NANOCRYSTAL CAPPED WITH the glycine hydroxamate and the binding thereof to affinity biological molecules.

Few milligrams of nanocrystals powder are dissolved in heptane and mixed with water solution of glycine hydroxamate (0,1-0,001 M) under vigorous stirring. Approximately in one hour, the nanocrystals are extracted from the aliphatic layer due to bonding of the hydroxamate to the Zn-atoms on the nanocrystal surface. The aliphatic layer is further removed and nanocrystals are precipitated by adding methanol, ethanol, propanol or acetone. The precipitate is dried to powder, or dissolved in fresh portion of water for further manipulations (figure 2a).

The binding of such *water-soluble* nanocrystals with biomolecules of interest such as amino acids, peptides, proteins, monoclonal or polyclonal antibodies and their functional fragments, oligonucleotides, RNA, single or double-stranded DNA, RNA-DNA hybrid molecules, DNA triplexes and multiplexes and carbohydrates, eg sialic acids, etc. may be further proceeded as described in Bioconjugate techniques, 1996, Ed. Hermanson, Academic Press, using the free NH₂-group of the nanocrystal-attached hydroxamate as an active linker group as presented in figure 3a wherein the nanocrystal probe reacts with activated amino acids, peptides or polypeptides and R is amino acids, peptides, proteins, monoclonal or polyclonal antibodies and their functional fragments, oligonucleotides, RNA, single or double-stranded DNA, RNA-DNA hybrid molecules, DNA triplexes and multiplexes and carbohydrates, eg sialic acids, etc.
EXAMPLE 3 :
FABRICATION OF *WATER-SOLUBLE* NANOCRYSTAL CAPPED WITH THE DIETHYLENETRIAMINEPENTAKIS (METHYLPHOSPHONIC ACID) and the PROCEDURE OF BINDING THEREOF to affinity BIOLOGICAL molecules.

The solubilisation of nanocrystals with multidentate ligands of ethylenediamine groups is conducted via the procedure described in example 2 for glycine hydroxamate.

Briefly, few milligrams of nanocrystals are dissolved in heptane and mixed with water solution of diethylenetriaminepentakis (methylphosphonic acid) under vigorous stirring. In one hour, aliphatic layer is removed and nanocrystals are precipitated by alcohols or acetone and re-dissolved in fresh portion of water. (figure 2b) The binding of such *water-soluble* nanocrystals with biological molecules of the interest such as amino acids, peptides, proteins, monoclonal or polyclonal antibodies and their functional fragments, oligonucleotides, RNA, single or double-stranded DNA, RNA-DNA hybrid molecules, DNA triplexes and multiplexes and carbohydrates, eg sialic acids, etc. may be further proceeded as described in

Bioconjugate techniques, 1996, Ed. Hermanson, Academic Press, as presented in figure 3b wherein respectively the nanocrystal probe (1) reacts with 1-ethyl-3-(3-dimethylaminopropyl) carbodiimide hydrochloride (EDC) to form (2), then with cystamine as linking agent to form (3), further with a containing protein sulfhydryl to form (4), or with EDC to form (2'x0;), then with a primary amine containing molecule to form (3'x0;) wherein R and R' are the same as R in example 2.

Example 4 : fabrication of *water-soluble* nanocrystals by treatment thereof WITH THE SODIUM DODECYL SULFATE AND formation of bilayer around of nanocrystal shell, and the process of binding of linking AGENT (EDAC),. WHICH WAS EVER bounded with the affinity molecule and creation of conJugate WITH THE BIOMOLECULE.

Few milligrams of nanocrystals are dissolved in tetrahydrofurane to which sodium dodecylsulfate (SDS) is added. The relative molar concentration of nanocrystal/SDS/ is 1/1 to 1/1000. The mixture is stirred few hours and solvent is evaporated at room temperature. The resulting powder is dissolved in water under ultrasonic treatment (figure 2c).

The binding of such *water-soluble* nanocrystals with biological molecules of interest such as amino acids, peptides, proteins, monoclonal or polyclonal antibodies and their functional fragments, oligonucleotides, RNA, single or double-stranded DNA, RNA-DNA hymeric molecules, DNA triplexes and multiplexes and carbohydrates, eg sialic acids, ETC., may be further proceeded as described in Bioconjugate techniques, 1996, Ed. Hermanson, Academic Press, as presented in figure 3c wherein R is same as in example 2.

Example 5 : FABRICATION OF POLYMERIC *WATER-SOLUBLE* BEAD CAPPED WITH THE FARBOXYL GROUPS, COMPRISING one or more nanocrystals embedded within the polymeric matrix ; binding of LINKING AGENT AND AFFINITY MOLECULES TO THE B _AD AND creation of BIOCONJUGATE.

Few milligrams of nanocrystals are dissolved in a mixture of methylmethacrylate/hexylmethacrylate/methacrylic acid or methylmethacrylate/decylmethacrylate/methacrylic acid at various molar concentrations : 100/0/1 to 0/100/1. The radical initiator AIBN or its derivative is added to approximately 0,1-5% (w/w) and this solution is mixed with water to which 0,0001-0,1% (W/W) of SDS or HEXADECYLTRIMETHYLAMMONIUM bromide was added. Under vigorous stirring, the emulsion is polymerized at 60-90°C within few hours. Finally, polymeric beads are isolated by centrifugation and re-dissolved in fresh portion of water (figure 2d).

The binding of such *water-soluble* nanocrystals with biological molecules of interest such as amino acids, peptides, proteins, monoclonal or polyclonal antibodies and their functional fragments, oligonucleotides, RNA, single or double-stranded DNA, RNA-DNA hymeric molecules, DNA triplexes and multiplexes and carbohydrates, eg sialic acids, etc. may be further proceeded as described in Bioconjugate techniques, 1996, Ed. Hermanson, Academic Press, as presented in figure 3d wherein R is the same as in example 2.

Example 6 : USE OF THE WATR-NOLUBLE DOPED OR NNDOPED nanocrystal probes @S FOR DETECTION OF BIOLOGICAL SUBSTANCES and preparation of samples containing nanocrystal probes of the INVENTION AND RECORDING OF FLUORESCENCE-IMAGE O BIOLOGICAL t (living cell or in MTRO IMMUNOLOYICAL ASSAYT The figures 5a, 5b and 5c show examples of application of

the *water-soluble* nanocrystals of the invention for fluorescence ex-vivo imaging of biological object (monocytes treated with the water-solubilized nanocrystals) and the results of application of the antibodies-nanocrystals conjugates in the Western blot and dot-blot immunoassays for *ultrasensitive* detection of biological substances. The samples were prepared using conventional techniques and the experimental conditions are presented in the figures.

The cellular labelling with the help of the quantum dots according to the invention is illustrated in figure 5a.

As seen in figure 5c, antibodies-nanocrystals conjugates are used in the Western blot. The Western blot was treated with the primary topoisomerase I-SPECIFIC antibodies and further treated with the conjugates of the 4nm-diameter quantum dots with the secondary antibodies.

As seen in figure 5b, antibodies-nanocrystals conjugates are used in dot-blot immunoassays for *ultrasensitive* detection of biological substances.

Description Claims

CLAIMS 1. *Water-soluble* semiconductor nanocrystal comprising semiconductor core and shell as well as a cap of one or more additional compounds comprising water-solubilization agents, characterized in that the water-solubilization agent is chosen in the group consisting of : - HYDROXAMATES or derivatives of hydroxamic acid or a combination thereof, - multidentate complexing agents or a combination thereof, - A bilayer of a TOPO layer attached to the surface of the nanocrystal and an appropriate surfactant layer, - A polymeric bead comprising carboxylic groups or amino groups or a combination thereof at the surface of the bead comprising one or more nanocrystal embedded within, - A molecule of structural formula (R1) A-R2- { (R3) b (R4) CLOD- 2. *Water-soluble* semiconductor nanocrystal according to the claim 1, characterised in that the multidentate complexing agent includes derivatives of ethylenediamine, diethylenetriamine, triethylenetetramine, tetraethylenepentaamine including multidentate acids, amines, thiols, phosphines, phosphates, phosphin oxides or a combination thereof.

3 *Water-soluble* semiconductor nanocrystal according to the claim 1, characterized in that the molecule of structural formula (R1)a-R2- {(R3)b(R4)c}d is such as : R1 IS selected from the group consisting of heteroalkyl, heteroalkenyl, heteroalkynyl, -SR, -NHR, -NR2, -N (O) HR, - N (O) R2, -PHR, -PR2, -P (NR2), -P (O) R2, -P (O) (NR2) NR2, - P (O) (OR) POR, -P (O) OR, -P (S) (OR) OR, -P (S) OR, -P (S) SH, -P (S) SR, - C (S) SH, -C (S) SR wherein R is Li, Na, K; Rb, Cs, NH4, PH4, R2 is selected from a bond, branched or unbranched alkylene, a branched or unbranched alkenylene, a branched or unbranched heteroalkylene, a branched or unbranched heteroalkenylene, cycloalkyl, cycloalkenyl, cycloalkynyl, heterocyclic aryl and heteroaryl, R3 is selected from a branched or unbranched alkylene, a branched or unbranched alkenylene, a branched or unbranched heteroalkylene, a branched or unbranched heteroalkenylene, cycloalkyl, cycloalkenyl, cycloalkynyl, heterocyclic aryl and heteroaryl, R4 is selected from the group consisting of hydrogen, a carboxylate, a thiocarboxylate, an amine, an amide, an imine, an hydrazine, a sulfonate, a sulfoxide, a phosphate, a phosphonate, a phosphonium, an alcohol, a thiol, an ammonium, an alkyl ammonium, a nitrate, a sugar moiety and a five, six, seven, eight, nine, TEN-MEMBERED CYCLOALKYL, cycloalkenyl, cycloalkynyl, heterocyclic, aryl or heteroaryl, a being 1,2,3 or 4, b being 0,1,2 or 3, c being 0,1,2 or 3, d being 0,1,2 or 3.

4. **Water-soluble** semiconductor nanocrystal according to the claim 1, characterised in that the nanocrystal is doped with paramagnetic ions such as Mn^{2+} and other transition or rare-earth ions.

5. **Water-soluble** nanocrystal probe comprising a semiconductor nanocrystal, a water-solubilisation agent, a linking agent and an affinity moiety which is able to bound specifically to detectable biological substances, characterized in that the **water-soluble** nanocrystal is one according to one of the claims 1 to 4.

6. Probe according to the claim 5, characterized in that the linking agent is able to connect the **water-soluble** nanocrystal or the polymeric bead comprising one or more nanocrystals embedded within, with the affinity molecules including peptides, proteins, monoclonal or polyclonal antibodies and their FUNCTIONAL fragments, oligonucleotides, RNA, single and double stranded DNA, RNA-DNA hybrid molecules, DNA triplexes and multiplexes and carbohydrates which are able to bound specifically to detectable biological substances e. g. proteins, oligonucleotides, DNA, RNA, viruses, bacteria, cells, including living cells and tissues.

7. Probe according to the claims 5 and 6, characterized in that the water-solubilisation agent is also the linking agent.

8. Process for the preparation of a **water-soluble** nanocrystal according to the claims 1 and 4, characterised in that : a nanocrystal powder is dissolved in an aliphatic solvent and then mixed with a water solution of derivative of hydroxamic acid, the aliphatic layer containing the nanocrystals is extracted and, the nanocrystals are precipitated by addition of an alcohol solvent, the precipitate being then dried to powder or dissolved in water.

9. Process for the preparation of a **water-soluble** nanocrystal according to the claim 1,2 and 4, characterised in that : nanocrystal powder is dissolved in an aliphatic solvent and then mixed with a water solution of multidentate complexing agents or a combination thereof, the aqueous layer containing the nanocrystals is extracted and, the nanocrystals are precipitated by addition of an alcohol solvent, the precipitate being then dissolved in water.

10. Process for the preparation of a **water-soluble** nanocrystal according to one of the claims 1 and 4, characterised in that : nanocrystals are dissolved in tetrahydrofuran to which an appropriate surfactant layer such as sodium dodecyl sulfate (SDS) is added, the mixture is stirred few hours, the solvent is evaporated at room temperature and the resulting powder is dissolved in water under ultrasound treatment.

11. Process for the preparation of polymeric **water-soluble** bead capped with carboxylic groups, comprising one or more nanocrystals embedded within the polymeric matrix according to one of the claim 1 and 4, characterised in that : nanocrystals are dissolved in a mixture of appropriate monomers, a radical initiator is added, the emulsion is prepared in water, containing surfactant, and polymerised at 60-90°C within few hours under vigorous stirring, the polymeric beads being isolated by centrifugation and re-dissolved in water.

12. Process for the fabrication of doped nanocrystals with paramagnetic ions according to the claim 4, Characterised in that : TOPO is dried and degassed at 180°C for approximately 1 hour under argon atmosphere, a solution of elemental semiconductors and the paramagnetic ions in TOP to this melt at 350°C is added the reaction mixture is then cooled to 300°C and a

second solution of semiconductors is added and the reaction mixture is then cooled to 105°C, finally the semiconductor core and shell doped with paramagnetic ions are precipitated and washed with methanol and dissolved with hexane, heptane or tetrahydrofuran or dried to powder.

13. Method of detection of biological substances by registration of EPR signal from paramagnetic ions incorporated into the nanocrystals according to the claim 4.

14. Method of detection of biological substances by registration of fluorescence signal from the nanocrystal according to anyone of the claims 1 and 4.

15. Method of detection of biological substances by registration of a combination of fluorescence signal and EPR signal from paramagnetic ions incorporated into the nanocrystals according to the claims 1 and 4.

16. Method of detection of biological substances by the construction of the images of biological substances by fluorescence or EPR microscopy or by a combination thereof from the nanocrystals according to the claims 1 and 4.

Description Claims




FIGURE 1




FIGURE 2a




FIGURE 2b




FIGURE 2c

5/14




FIGURE 2d

6/14




FIGURE 3a

7/14






FIGURE 3b, Page 1

8/14

4



OR



3'




FIGURE 3b , Page 2

Phosphate containing macromolecule
(oligonucleotide 5'phosphate)

EDC




FIGURE 3c

10/14




FIGURE 3d





FIGURE 4.

12/14

Cellular Labeling with the Help of the Quantum Dots

Phagocytosis of the water-solubilized nanoparticles by the monocytes



Expression of the human DNA Topoisomerase I in the sf9 insect cells within the baculovirus system, detected with the conjugates of secondary antibodies with the 4 nm-diameter Quantum Dots

Dot-blots of the lysates of the insect cells infected with the recombinant baculovirus vector with the gene of human DNA topoisomerase I. Secondary antibodies (polyclonal immunoglobulins, Sigma, were reduced with the 2-mercaptoethylamine (Pierce), conjugated with the Quantum dots and used for detection in the dilutions of 1 : 100 (1), 1 : 200 (2), 1 : 300 (3), 1 : 400 (4), 1 : 500 (5), and 1 : 1000 (6).




FIGURE 5. b

14/14

Polyacrylamide gel electrophoresis (left) and Western-blot (right) of the lysate of insect sf9 cells overexpressing the human DNA topoisomerase I within the baculovirus system

Western was treated with the primary topoisomerase I-specific antibodies and further treated with the conjugates of the 4 nm-diameter Quantum Dots with the secondary antibodies




FIGURE 5 c

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.